

## LOCTITE® DRI STS

Known as LOCTITE® Dri-Loc STS™  
August 2016

### PRODUCT DESCRIPTION

LOCTITE® DRI STS provides the following product characteristics:

<b>Technology</b>	Acrylic
<b>Chemical Type</b>	Methacrylate ester
<b>Appearance (uncured)</b>	Creamy light blue dispersion <sup>LMS</sup>
<b>Components</b>	Two-component
<b>Viscosity</b>	Medium
<b>Cure</b>	Anaerobic
<b>Application</b>	Thread sealing
<b>Strength</b>	Medium

LOCTITE® DRI STS is a pre-applied adhesive/sealant coating for threaded fasteners and fittings. The product, as a pre-applied film, is dry-to-the-touch and remains an inert coating until assembly. During assembly of the fitting/fastener, a microencapsulated activator is then released, thereby initiating the cure process. Straight Thread Sealant™ possesses high lubricity to minimize friction for a more controllable torque tension relationship. The resin fills all the voids in the threads and cures to securely lock and seal the assembly. Straight Thread Sealant™ prevents loosening through vibration to provide locking and sealing of straight threaded assemblies including: ring gear bolts, carburetor screws, transmission nuts, head bolts, truck axle bolts, tower bolts, transmission bolts and pipe plugs and fittings.

**NOTE:** LOCTITE® DRI STS is not recommended for use on copper or brass surfaces.

### TYPICAL PROPERTIES OF UNCURED MATERIAL

Flash Point - See SDS

Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):

Spindle 5, speed 2 rpm 35,000 to  
100,000<sup>LMS</sup>

On Part Life, years 4


### TYPICAL CURING PERFORMANCE

Fixture Time, minutes 10

On Part Life, years 4

### Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The graph below shows the breakaway strength developed with time on 3/8 x 16 nuts and bolts from different materials. compared to different materials and tested according to MIL-S-46163.



### TYPICAL PERFORMANCE OF CURED MATERIAL

#### Adhesive Properties

After 24 hours @ 22 °C

On - Torque, ISO 10964:

3/8 x 16 phosphate and oil grade 2 nuts and grade 5 bolts N·m ≤0.6<sup>LMS</sup>  
(lb.in.) (≤5.3)

Breakaway Torque, ISO 10964:

3/8 x 16 phosphate and oil grade 2 nuts and grade 5 bolts N·m ≥17.0<sup>LMS</sup>  
(lb.in.) (≥150.4)

After 72 hours @ 22 °C

Breakaway Torque, ISO 10964:

3/8 x 16 phosphate and oil grade 2 nuts and grade 5 bolts N·m ≥22.6<sup>LMS</sup>  
(lb.in.) (≥200)

M10 x 1.5 Steel with Anti-Rust grade 10.9 bolts and grade 8 steel zinc plated nuts N·m 11  
(lb.in.) (94)

M10 x 1.5 Steel Zinc plated grade 10.9 bolts and grade 10 steel zinc plated nuts N·m 12  
(lb.in.) (105)

M10 x 1.5 Steel Magni 554 plated grade 8.8 bolts and grade 8 steel zinc plated nuts N·m 14  
(lb.in.) (120)

**Prevail Torque, ISO 10964:**

3/8 x 16 phosphate and oil grade 2 nuts and grade 5 bolts	N·m (lb.in.)	≥7.9 <sup>LMS</sup> (≥69.9)
M10 x 1.5 Steel with Anti-Rust grade 10.9 bolts and grade 8 steel zinc plated nuts	N·m (lb.in.)	7.6 (67)
M10 x 1.5 Steel Zinc plated grade 10.9 bolts and grade 10 steel zinc plated nuts	N·m (lb.in.)	8.1 (72)
M10 x 1.5 Steel Magni 554 plated grade 8.8 bolts and grade 8 steel zinc plated nuts	N·m (lb.in.)	8.4 (74)

**Breakloose Torque, ISO 10964, Input Torque = 50 N·m:**

M10 x 1.5 Steel with Anti-Rust grade 10.9 bolts and grade 8 steel zinc plated nuts	N·m (lb.in.)	45 (395)
M10 x 1.5 Steel Zinc plated grade 10.9 bolts and grade 10 steel zinc plated nuts	N·m (lb.in.)	42 (375)
M10 x 1.5 Steel Magni 554 plated grade 8.8 bolts and grade 8 steel zinc plated nuts	N·m (lb.in.)	39 (350)

**Total Coefficient of Friction (DIN 946):**

These values are only valid for tested combinations of fasteners. Friction coefficients are based on :

- Surface finish
- Surface roughness
- Fitting quality of bearing surface
- Lubrication
- Assembly conditions (e.g. screw-in speed)
- Design (e.g. dimensions, geometry of threads)

M10 x 1.5 Steel with Anti-Rust grade 10.9 bolts and grade 8 steel zinc plated nuts	0.15
M10 x 1.5 Steel Zinc plated grade 10.9 bolts and grade 10 steel zinc plated nuts	0.14
M10 x 1.5 Steel Magni 554 plated grade 8.8 bolts and grade 8 steel zinc plated nuts	0.11

**TYPICAL ENVIRONMENTAL RESISTANCE**


Cured for 72 hours @ 22 °C

Breakaway Torque, MIL-S-46163:


3/8 x 16 phosphate and oil nuts and bolts

**Hot Strength**

Tested at temperature

**Heat Aging**

Aged at temperature indicated and tested @ 22 °C

**Chemical/Solvent Resistance**

Aged under conditions indicated and tested @ 22 °C.

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
Motor oil	125	105	105	102
Motor oil	87	119	124	126
Gasoline (unleaded)	22	109	116	118
Brake fluid	22	105	109	110
1,1,1 Trichloroethane	22	103	116	115
Water/glycol 50/50	87	124	116	110

**CORROSIVITY**

LOCTITE® DRI STS may stain or discolor some metals. However, this does not effect its performance or the materials to which it is applied.

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

**Directions for use:****Application Method:**

LOCTITE® DRI STS is applied to threaded parts by authorized converters who have automatic fastener cleaning, feeding, coating, rust proofing and drying equipment. Quantities can be handled promptly with minimum turnaround time. Sample bolts should be sent to the nearest authorized converter where they will coat your

parts and return them to you for evaluation. **SAMPLE TESTS ARE RECOMMENDED TO OBTAIN DESIRED RESULTS ON YOUR PARTS.** Contact the nearest LOCTITE® Technical Service Center for the authorized converter nearest to you.

### Loctite Material Specification<sup>LMS</sup>

LMS dated May 28, 2004. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is,

therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

### Reference 0.5